

OXIDIZED BITUMEN

Technical data sheet



Description

Product does not contain any dangerous substances.

Technical data

Parameters	Norms		Measure units	Value
	C.N.R.	ASTM		
Penetration DOW at 25 °C 100 gr/5 sec	C.N.R. B.U.24	ASTM D. 5 - 65	dmm	8
Softening point	C.N.R. B.U.35	ASTM D.36 - 66	P.A. °C	95
Breaking point FRASS	C.N.R. B.U. 43	IP 80/53	Min. °C	-6
Solubility*	C.N.R. B.U. 48	ASTM D.2442 - 66	Min. % weight	99,5
Cleveland open vase*	C.N.R. B.U. 72	ASTM 92/66	Min. °C	> 270
Density at 25/25 °C	C.N.R. B.U. 67	ASTM D.2415 - 66	-	1.00 - 1.03
Volatility at 163 °C	C.N.R. B.U. 50	ASTM D. 6 - 67	Max % weight	< 0.3
Penetration at 25 °C after volatility test	C.N.R. B.U. 24	ASTM D. 5 - 65	dmm	-
Weight tolerance			%	+/- 3%

* Statistical sampling every 180 days.

Pluvitec reserves the rights to change or modify the nominal values without prior notice or advice.